

Mueller Streamline Co. Headquarters

150 Schilling Blvd Suite 201

Collierville, Tennessee 38017

United States

Phone: 901 753 3200

Mueller Streamline Co. International

525 Okeechobee Blvd Suite 860

West Palm Beach, FL 33401

United States

Phone: 561 273 8300

ITEM # X 02072, 90º LONG RADIUS ELBOW, C X C, 2-1/8" X 2-1/8"

Streamline® XHP Copper-Iron Fittings for use in refrigeration applications. Available sizes ranging from 3/8" to 2-1/8" for continuous 130 BAR / 1885 PSI pressure ratings at 120°C / 250°F.



<u>Specifications | Dimensions | Details</u>

Spe	fications		
	Weight	2.19 lb	
	Material ¹	COPPER-IRON	
	Operating Temperature [Max]	250 °F	
	Operating Pressure [Max]	1885 psi	
	End Type	Cup (Braze)	
	End Size	2 1/8 in	

Second End Type	Cup (Braze)
Second End Size	2 1/8 in
Standards	Copper-iron (CuFe2P) UNS C19400 130 BAR / 1,885 PSI 120°C / 250°F

Overall Length4.87 inOverall Height4.87 inOverall Width2.42 in	Dimensions	imensions –				
	Overall Length	4.87 in				
Overall Width 2.42 in	Overall Height	4.87 in				
	Overall Width	2.42 in				
X 2.56 in	X	2.56 in				

Details -					
Qty Pcs / Bag	1				
Master Qty Pcs / Box	30				
Mueller Description	2-1/8 OD LR 90 ELL				
Key Specifications	Streamline® XHP Copper Fittings is third party verified through Underwriters Laboratories for max operating temperature of 250° F (120° C) and continuous operating pressure of 1740 psi (120 Bar).				
Installation	Streamline® XHP copper material was developed for use with high pressure refrigerants. Compared to conventional pure copper Cu-DHP (99.9% Cu; UNS C12200), Streamline® XHP material is a CuFe2P alloy (2% iron; UNS C19400). This material's wettability is comparable to that of Cu-DHP. Streamline® XHP TM is not subject to any restrictions for the selection of brazing alloy. Commonly used brazing filler metal types such as BCup Alloy (may contain 0%-30% Silver – Ag) or Bag Alloy (may contain anywhere between 24% and 93% Silver – Ag) can be used. The brazing alloy chosen must be clarified with the brazing alloy supplier for each specific application. The selection of brazing alloy may depend on a few factors: applicable codes, OEM specifications,				

vibration, and operating temperatures.

 1 Streamline® XHP $^{\text{TM}}$ Copper Fittings shall be made from material in compliance with UNS C19400 grade of copper.